

# **Technical Data Sheet**

info.polyethylene@versalis.eni.com

## **CLEARFLEX® H&T**

CHH GO

**VLDPE** 

Very low density polyethylene

Clearflex CHH G0 is a linear low density polyethylene, with antioxidants, characterised by a very low density (VLDPE).

The resin has an excellent compatibility with polyolefins and fillers.

### **Main Applications**

Clearflex CHH G0 is recommended for applications in which soft touch and flexibility are required, for improvement of impact resistance when used as additive in blend with other polyolefins formulated with or without mineral fillers.

in Properties			
Resin Properties	Value	Unit	Test Method
Melt Flow Rate (190 °C/2.16 kg)	1.5	g/10min	ISO 1133
Melt Flow Rate (190 °C/5 kg)	-	g/10min	ISO 1133
Melt Flow Rate (190 °C/21.6 kg)	-	g/10min	ISO 1133
Density	0.887	g/cm3	ISO 1183
Melting Point	102	°C	Internal method
Brittleness temperature	<- 70	°C	ASTM D 746
Vicat softening point (1 kg)	45	°C	ISO 306/A
Film Properties *	Value	Unit	Test Method
Tensile stress at yield MD	-	MPa	ISO 527-3
Tensile stress at yield TD	-	MPa	ISO 527-3
Tensile stress at break MD	17	MPa	ISO 527-3
Tensile stress at break TD	-	MPa	ISO 527-3
Elongation at break MD	> 800	%	ISO 527-3
Elongation at break TD	-	%	ISO 527-3
1% Secant modulus MD	-	MPa	ISO 527-3
1% Secant modulus TD	-	MPa	ISO 527-3
Elmendorf tear resistance MD	-	N/mm	ISO 6383-2
Elmendorf tear resistance TD	-	N/mm	ISO 6383-2
Impact resistance F50 (Dart Drop Test)	-	g	ISO 7765-1/A
Dynamic coefficient of friction (COF)	-	-	ISO 8295
Haze	-	%	ISO 14782
Gloss, 45°	-	%	ASTM D 2457
Recommended film thickness	-	micron	-

<sup>(\*)</sup> Typical value for a cast film extruded at 220°-270°C. Actual properties are typical and may vary depending upon operating conditions and additive package.

#### **Processing notes**

Clearflex CHH G0 is easily processable. Melt temperature should be between 190°C and 230°C.

#### Storage and Handling

Clearflex CHH G0 is supplied in pellet form. This material may readily be conveyed and bulk fed through equipment designed for conventional pelletised polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping should be practised throughout your facility.

The product should be stored in dry conditions at temperatures below 50°C and protected from sunlight. Improper storage can initiate degradation which results in odour generation, colour changes and can have negative effects on the physical properties of the product.

Before using this product it is recommended to read and understand the relevant Safety Data Sheet.

#### **Availability**

Contact the versalis sales office nearest to you regarding availability and your specific application requirements.

#### **Food Contact Status**

Clearflex CHH G0 complies with the rules and regulations of the European Union, as well as other countries, regarding the use of plastic materials in food contact applications. Certificates of compliance are available upon request.

#### **TECHNICAL SERVICE**

versalis S.p.A. Piazza Boldrini, 1 20097 S.Donato Milanese, Italia Tel. +39 02 520.32087 Fax +39 02 520.52052 Versalis International SA succursale française Port 4531 Route des Dunes - BP 59 F-59279 Mardyck versalis S.p.A. Via Taliercio, 14 46100 Mantova, Italia Tel. +39 0376 305667 Fax +39 02 52043

#### **HEADQUARTER**

versalis S.p.A. Piazza Boldrini, 1 20097 S.Donato Milanese, Italia Tel. +39 02 520.32087 Fax +39 02 520.52052

IMPORTANT: please consult the relevant safety data sheet for more detailed information. The information and data presented herein are to the best of our knowledge true and accurate but no warranty or guarantee, expressed or implied, is made nor is any liability accepted with respect to the use of such information and data.

versalis is available to provide the guaranteed values for each product on demand.