



## CLEARFLEX® H&T

## FHH 508

LLDPE

Linear low density polyethylene

Clearflex H&T FHH 508 is an octene copolymer linear medium density polyethylene, with antioxidants, suitable for blown film extrusion.

Films obtained from Clearflex H&T FHH 508 show good optical properties, high rigidity, high temperature resistance and excellent sealing properties.

### Main Application

For its excellent optical properties and sealing performances, together with a very low gel content, Clearflex H&T FHH 508 is the ideal choice for the production of lamination films. Due to its softening point, Clearflex H&T FHH 508 is especially recommended for flexible packaging that have to withstand heat cycles such as cook-in films.

### Main Properties

Resin Properties	Value	Unit	Test Method
Melt Flow Rate (190 °C/2.16 kg)	1.5	g/10min	ISO 1133
Melt Flow Rate (190 °C/5 kg)	-	g/10min	ISO 1133
Melt Flow Rate (190 °C/21.6 kg)	-	g/10min	ISO 1133
Density	0.935	g/cm <sup>3</sup>	ISO 1183
Melting Point	127	°C	Internal method
Brittleness temperature	< - 70	°C	ASTM D 746
Vicat softening point (1 kg)	117	°C	ISO 306/A

Film Properties *	Value	Unit	Test Method
Tensile stress at yield MD	16	MPa	ISO 527-3
Tensile stress at yield TD	18	MPa	ISO 527-3
Tensile strenght at break MD	50	MPa	ISO 527-3
Tensile strenght at break TD	40	MPa	ISO 527-3
Elongation at break MD	600	%	ISO 527-3
Elongation at break TD	900	%	ISO 527-3
1% Secant modulus MD	430	MPa	ISO 527-3
1% Secant modulus TD	500	MPa	ISO 527-3
Elmendorf tear resistance MD	30	N/mm	ISO 6383-2
Elmendorf tear resistance TD	130	N/mm	ISO 6383-2
Impact resistance F50 (Dart Drop Test)	70	g	ISO 7765-1
Dynamic coefficient of friction (COF)	> 0.5	-	ISO 8295
Haze	13	%	ISO 14782
Gloss, 45°	60	%	ASTM D 2479
Recommended film thickness	10 ÷ 50	micron	-

\* Typical value for a film extruded between 190°-230°C, with BUR 2.5, thickness 25 µm. Actual properties are typical and may vary depending upon operating conditions and additive package.

## Processing notes

Clearflex H&T FHH 508 is easily processable using blown film technology. Melt temperature should be between 190°C and 230°C. Recommended thickness: 10 - 50 µm.

## Storage and Handling

Clearflex H&T FHH 508 is supplied in pellet form. This material may readily be conveyed and bulk fed through equipment designed for conventional pelletised polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping be practised throughout your facility.

The product should be stored in dry conditions at temperatures below 50°C and protected from sunlight.

Improper storage can initiate degradation which results in odour generation, colour changes and can have negative effects on the physical properties of the product.

Before using this product it is recommended to read and understand the relevant Safety Data Sheet.

## Availability

Contact the Versalis sales office nearest to you regarding availability and your specific application requirements.

## Food Contact Status

Clearflex H&T FHH 508 complies with the rules and regulations of the European Union, as well as other countries, regarding the use of plastic materials in food contact applications. Certificates of compliance are available upon request.

---

### TECHNICAL SERVICE

Versalis S.p.A.  
Piazza Boldrini, 1  
20097 S. Donato Milanese, Italia  
Tel. +39 02 520.1  
Fax + 39 02 520.42436

Polimeri Europa SAS  
1 Route des Dunes BP 59  
F-59279 MARDYCK - France  
Tel. +33 3 28235515  
Fax +33 3 28235520

Versalis S.p.A.  
Via Taliercio, 14  
46100 Mantova, Italia  
Tel. +39 0376 305667  
Fax +39 02 52043

---

### HEADQUARTER

Versalis S.p.A.  
Piazza Boldrini, 1  
20097 S. Donato Milanese, Italia  
Tel. +39 02 520.1  
Fax + 39 02 520.42436

---

**IMPORTANT:** please consult the relevant safety data sheet for more detailed information. The information and data presented herein are to the best of our knowledge true and accurate but no warranty or guarantee, expressed or implied, is made nor is any liability accepted with respect to the use of such information and data.

Versalis is available to provide the guaranteed values for each product on demand.