

Technical Data Sheet

info.polyethylene@versalis.eni.com

FLEXIRENE ®

FF 25 U

LLDPE

M

Linear low density polyethylene

Flexirene FF 25 U is a LLDPE with butene copolymer produced with Gas Phase technology, with antioxidants, suitable for blown film extrusion.

Flexirene FF 25 U is characterised by a high elongational viscosity leading to a good bubble stability during extrusion.

Main Applications

Flexirene FF 25 U is recommended for the production of agricultural film, heavy duty bags, in blend or coextrusion with LDPE.

| Main Properties | | | |
|--|---------|---------|--------------------|
| Resin Properties | Value | Unit | Test Method |
| Melt Flow Rate (190 °C/2.16 kg) | 0.7 | g/10min | ISO 1133 |
| Melt Flow Rate (190 °C/5 kg) | - | g/10min | ISO 1133 |
| Melt Flow Rate (190 °C/21.6 kg) | - | g/10min | ISO 1133 |
| Density | 0.920 | g/cm3 | ISO 1183 |
| Melting Point | 120 | °C | Internal method |
| Brittleness temperature | <- 70 | °C | ASTM D 746 |
| Vicat softening point (1 kg) | 98 | °C | ISO 306/A |
| | | | |
| Film Properties * | Value | Unit | Test Method |
| Tensile stress at yield MD | 11 | MPa | ISO 527-3 |
| Tensile stress at yield TD | 11 | MPa | ISO 527-3 |
| Tensile stress at break MD | 45 | MPa | ISO 527-3 |
| Tensile stress at break TD | 32 | MPa | ISO 527-3 |
| Elongation at break MD | 580 | % | ISO 527-3 |
| Elongation at break TD | 800 | % | ISO 527-3 |
| 1% Secant modulus MD | 200 | MPa | ISO 527-3 |
| 1% Secant modulus TD | 210 | MPa | ISO 527-3 |
| Elmendorf tear resistance MD | 25 | N/mm | ISO 6383-2 |
| Elmendorf tear resistance TD | 180 | N/mm | ISO 6383-2 |
| Impact resistance F50 (Dart Drop Test) | 100 | g | ISO 7765-1/A |
| Dynamic coefficient of friction (COF) | > 0.5 | - | ISO 8295 |
| Haze | 12 | % | ISO 14782 |
| Gloss, 45° | 55 | % | ASTM D 2457 |
| Recommended film thickness | 15 ÷ 50 | micron | - |

^(*) Typical value for a film extruded between 190°-230°C, with BUR 2.5, thickness 25 μm. Actual properties are typical and may vary depending upon operating conditions and additive package.

Flexirene ® is a registered trademark of versalis

Processing notes

Flexirene FF 25 U is easily processable using blown film technology. Melt temperature should be between 190° C and 230°C.

Recommended thickness: 15 - 50 µm.

Storage and Handling

Flexirene FF 25 Uis supplied in pellet form. This material may readily be conveyed and bulk fed through equipment designed for conventional pelletised polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping should be practised throughout your facility.

The product should be stored in dry conditions at temperatures below 50°C and protected from sunlight. Improper storage can initiate degradation which results in odour generation, colour changes and can have negative effects on the physical properties of the product.

Before using this product it is recommended to read and understand the relevant Safety Data Sheet.

Availability

Contact the versalis sales office nearest to you regarding availability and your specific application requirements.

Food Contact Status

Flexirene FF 25 U complies with the rules and regulations of the European Union, as well as other countries, regarding the use of plastic materials in food contact applications. Certificates of compliance are available upon request.

TECHNICAL SERVICE

versalis S.p.A. Piazza Boldrini, 1 20097 S.Donato Milanese, Italia Tel. +39 02 520.32087 Fax +39 02 520.52052 Versalis International SA succursale française Port 4531 Route des Dunes - BP 59 F-59279 Mardyck versalis S.p.A. Via Taliercio, 14 46100 Mantova, Italia Tel. +39 0376 305667 Fax +39 02 52043

HEADQUARTER

versalis S.p.A. Piazza Boldrini, 1 20097 S.Donato Milanese, Italia Tel. +39 02 520.32087 Fax +39 02 520.52052

IMPORTANT: please consult the relevant safety data sheet for more detailed information. The information and data presented herein are to the best of our knowledge true and accurate but no warranty or guarantee, expressed or implied, is made nor is any liability accepted with respect to the use of such information and

versalis is available to provide the guaranteed values for each product on demand.