

Technical Data Sheet

www.versalis.eni.com

info.polyethylene@versalis.eni.com

ERACLENE ®

MP 90 U

HDPE

High density polyethylene

Eraclene MP 90 U is a high density polyethylene homopolymer resin (HDPE) with antioxidants, suitable for injection moulding application.

Eraclene MP 90 U has a narrow molecular weight distribution and a high density which makes it the perfect choice for manufacts requiring outstanding rigidity, warpage resistance and toughness.

Main Application

Eraclene MP 90 U is specifically designed for bottle crates, cases, toys, trays and other similar objects requiring rigidity.

Main Properties

Resin Properties	Value	Unit	Test Method
Melt Flow Rate (190 °C/2.16 kg)	7	g/10min	ISO 1133
Melt Flow Rate (190 °C/5 kg)	20	g/10min	ISO 1133
Melt Flow Rate (190 °C/21.6 kg)	-	g/10min	ISO 1133
Density	0.960	g/cm3	ISO 1183
Melting point	137	°C	Internal method
Brittleness temperature	<- 60	°C	ASTM D 746
Vicat softening point (1 kg)	128	°C	ISO 306/A

Mechanical Properties *	Value	Unit	Test Method
Tensile stress at yield	30	MPa	ISO 527
Tensile stress at break	17	MPa	ISO 527
Tensile strain at yield	-	%	ISO 527
Elongation at break	400	%	ISO 527
Flexural modulus	1450	MPa	ISO 178
Hardness Shore D	69	-	ISO 868 A
Falling Weight:	-	J/mm	ISO 6603-2
Izod impact strength, notched	100	J/m	ISO 180/A
Environmental Stress Cracking Resistance (ESCR)	-	h	ASTM 1693/B

^(*) Values are referred to compression moulded specimens. Actual properties are typical and may vary depending upon operating conditions.

^{(**) 100%} surface-active agent – Condition B.

Processing notes

 $\label{lem:eq:conventional} \ \, \text{Eraclene MP 90 U is readily processable by conventional injection moulding equipment with excellent results.}$

Typical processing conditions (*)

Temperature profile of the barrel (°C) 190 - 260 Temperature of the mould (°C) 10 - 40

(*) Processing conditions are depending on several parameters: the shape of the part to be manufactured, the localisation of the injection point, the injection moulding machine and the cooling of the mould.

Storage and Handling

Eraclene MP 90 U is supplied in pellet form. This material may readily be conveyed and bulk fed through equipment designed for conventional pelletised polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping should be practised throughout your facility.

The product should be stored in dry conditions at temperatures below 50°C and protected from sunlight.

Improper storage can initiate degradation which results in odour generation, colour changes and can have negative effects on the physical properties of the product.

Before using this product it is recommended to read and understand the relevant Safety Data Sheet.

Availability

Contact the versalis sales office nearest to you regarding availability and your specific application requirements.

Food Contact Status

Eraclene MP 90 U complies with the rules and regulations of the European Union, as well as other countries, regarding the use of plastic materials in food contact applications. Certificates of compliance are available upon request.

TECHNICAL SERVICE

versalis S.p.A. Piazza Boldrini, 1 20097 S.Donato Milanese, Italia Tel. +39 02 520.32087

Fax +39 02 520.52087

Versalis International SA succursale française Port 4531 Route des Dunes - BP 59

F-59279 Mardyck Tel.: +33328235515 Fax: +33328235520 versalis S.p.A. Via Taliercio, 14 46100 Mantova, Italia Tel. +39 0376 305667 Fax +39 02 52043

HEADQUARTER

versalis S.p.A. Piazza Boldrini, 1 20097 S.Donato Milanese, Italia Tel. +39 02 520.32087 Fax +39 02 520.52052

IMPORTANT: please consult the relevant safety data sheet for more detailed information. The information and data presented herein are to the best of our knowledge true and accurate but no warranty or guarantee, expressed or implied, is made nor is any liability accepted with respect to the use of such information and data.

versalis is available to provide the guaranteed values for each product on demand.